



Krishna Tissues Private Limited
Burdwan Katwa Road, Narja More, Mouza - Aorachawk & Narja
P.O. - Bhatar, Dist - Burdwan, Pin - 713125, West Bengal, India
E-mail : krishnatissues@vsnl.net / exdm@krishnatissues.com
"STAR EXPORT HOUSE" Recognised by Govt. of India

1ST SEPTEMBER, 2017

SPECIFICATIONS OF LIGHT GSM KRAFT

S.NO.	PROPERTY	UNIT	PRODUCT RANGE	
01	Basis Weight	g/m ²	80	95
02	Moisture	%	6.0-7.5	6.0-7.5
03	Bulk	cc/g	1.4-1.5	1.4-1.5
04	Tear Strength	MD	600	720
		CD	720	880
05	Tear Strength	MD	7.0	7.0
		CD	9.0	9.0
06	Tensile Strength	MD	5.11	6.24
		CD	2.36	2.88
07	Tensile Index	MD	63	63
		CD	29	29
08	Stretch (Elongation)	MD	1.7	1.7
		CD	4.0	4.0
09	TEA (Tensile Energy Absorption)	MD	65	80
		CD	84	104
10	TEA INDEX	MD	0.8	0.8
		CD	1.1	1.1
11	Burst Strength	KPa	260	310
12	Burst Index	Kpa.m ² /g	3.2	3.2
13	Pososity (Air resistance GURLEY)	Sec/100ml	25	25
14	Cobb (60 seconds) TS	g/m ²	28	28
15	Cobb (60 seconds) WS	g/m ²	30	30

NOTE : All the above property values are ± 5% as per TAPPI standard.



MANUFACTURER OF FOLLOWING ITEMS

- ◆ Coated / Uncoated White Top Kraft Liner ◆ Coated Duplex Board
- ◆ Kraft Liner Board ◆ Test Liner Kraft ◆ Fluting Medium Paper
- ◆ Sack Kraft ◆ Carry Bag Kraft

